

Application

This material, also known as lead alumina bisilicate, is specially formulated for use in pottery and wall-tile glazes. It is also used in low-loss dielectrics and reflective highway signs. Lead bisilicate is extremely resistant to leaching by dilute acids, including gastric juices, which reduces its toxicity and offers the maximum safety of any of the lead products. It is available in either granulated or ground form.

Physical Properties

Color.....Very white yellow
 Form.....Granulated or ground
 Specific Gravity.....4.60 - 4.65
 Melting Point.....788 - 816°C. (1450 - 1501°)
 Coefficient of Expansion..... 7.1×10^{-6}
 Refractive Index.....1.72 - 1.74

Trace Elements

Element	Maximum (%)	Typical (%)
Fe ₂ O ₃	0.0130	0.0080
ZnO	0.0008	0.0004
Cu ₂ O	0.0006	0.0003
Ag	0.0014	0.0007
Bi ₂ O ₃	0.0300	0.0025
As ₂ O ₅ , Sb ₂ O ₃ , SnO ₂	0.0009	<0.0005
Ni, Te, Th, Cd	0.0006	<0.0004
Co, Cr, Mn, Se	0.0002	<0.0001

Chemical Composition

PbO (litharge)	65 +/- 0.8%
SiO ₂ (silica)	34 +/- 0.8%
Al ₂ O ₃ (alumina)	1 +/- 0.5%

Typical Screen Analysis (U.S. Standard Sieve)	Granular (%)	Ground (%)
greater than 3 mesh	0	0
between 3 - 10 mesh	1.3	0
between 10 - 20 mesh	81.3	0
between 20 - 40 mesh	10.0	0
between 40 - 80 mesh	134.8	0
between 80 - 100 mesh	2.6	1
between 100 - 200 mesh	0	1.2
Between 200 - 325 mesh	0	7.8
Less than 325 mesh	0	90.0

Packaging
50 lb. / 22.68 kg Paper bags
Special packaging available upon request

Note

This data sheet illustrates typical values for this product. If specific characteristics are required that are different from these values, please contact your area sales representative.



A division of Hammond Group, Inc.

1414 Field St. Hammond, IN 46320
 T+ (219) 931-9360 F+(219) 931-2140
 Email: info@hammondlead.com